

## Stein- und Mörtelverbrauch von Lehmsteine

| Bezeichnung |             | Steinverbrauch/m <sup>2</sup> |         |        | Mörtelverbrauch<br>Nassmörtel Liter/pro m <sup>2</sup> |      |      |
|-------------|-------------|-------------------------------|---------|--------|--|------|------|
|             |             | Wandstärke                    |         |        | Wandstärke   |      |      |
|             |             | 11,5                          | 24,0    | 17,5   | 11,5   | 24,0 | 17,5 |
| DF          | 240x115x52  | 63 St.                        | 126 St. |        | 29   | 80   |      |
| NF          | 240x115x71  | 48 St.                        | 96 St.  |        | 27   | 75   |      |
| 2 DF        | 240x115x113 | 32 St.                        | 64 St.  |        | 25   | 60   |      |
| 3 DF        | 240x175x113 |                               | 43 St.  | 32 St. |  | 55   | 35   |
| 8 DF        | 498x115x238 | 8 St.                         |         |        | 10   | 21   |      |
| 12 DF       | 498x175x238 |                               |         | 8 St.  |  |      | 20   |